

# PREPRUFE<sup>®</sup> DLM

Mono-component environmentally and EHS friendly detailing liquid membrane for use with GCP Applied Technologies waterproof membranes

---

## Product Applications

PREPRUFE<sup>®</sup> DLM is a damp-concrete tolerant and monocomponent liquid membrane (EHS Friendly), which does not require mixing and cures using air moisture.

PREPRUFE<sup>®</sup> DLM is caulk applied, and is supplied in 600ml sausages.

Coverage is approx. 2.5 litres per m<sup>2</sup> at 2.5 mm thickness

### Applications:

- pile terminations
- pipe penetrations
- membrane continuity through masonry
- internal corners
- difficult details

## Advantages

- **Liquid applied** – conforms to irregular profiles
- **Waterproof** – resistant to water vapour and water pressure
- **Mono-component** – no need of mixing on site
- **Seamless** – joint free membrane
- **Damp concrete tolerant**
- **Odourless** - improved workability in indoor environment
- **Cold applied** – no flame hazard
- **PREPRUFE<sup>®</sup> and BITUTHENE<sup>®</sup> membranes compatible** – complements both waterproofing membrane systems
- **Excellent hydrostatic head resistance performance** – passes 70m hydrostatic head resistance for thickness of 2.5mm
- **No pot life** – reduced wastage of unused material
- **Improved workability and trowel-ability** – faster application
- **Reduced material wastage**, aluminum packaging foil (reduced landfill fees)
- **No hazard pictograms** - the product is not classified according to the GHS/CLP regulation

## Installation

### Substrate Preparation

Apply it to clean, dirt free, frost-free surfaces at a coverage rate of 2.5 litres per m<sup>2</sup>. Allow the product to dry 60 minutes or until tack-free. Curing time may be longer in cold temperatures. Thick layer of product (except for fillet) should be avoided as this will lengthen the drying time.

Substrates should be dry or damped touch dry and free from surface condensation or standing water. All surfaces should be clean and free from dust, dirt, site debris, grease and any other contaminants that may compromise adequate adhesion.


### Installation Details

Ambient temperature shall be +5 °C and rising.

PREPRUFE<sup>®</sup> DLM may be used as a pointing surface sealer. A minimum overlap of the PREPRUFE<sup>®</sup> and BITUTHENE<sup>®</sup> sheet membrane of 50 mm shall be provided.

PREPRUFE<sup>®</sup> DLM is compatible with dry BITUTHENE<sup>®</sup> Primer W2 and the compound used on all PREPRUFE<sup>®</sup> and BITUTHENE<sup>®</sup> systems.

PREPRUFE<sup>®</sup> DLM will adhere to clean, dry metal substrates, PVC pipes and epoxy adhesive.



Supply	
PREPRUFE® DLM	600ml sausage
Shelf Life	12 months
BITUTHENE® Primer W2	5 litre bottle
<b>Ancillary Equipment</b>	
Solid barrel gun, spatula, trowel or float.	
<b>Approximate Coverage:</b>	<b>PREPRUFE® DLM 600 millilitre package coverage per linear meter:</b>
2.5 mm thick x 300 mm wide	0.8 Linear Meter per 600ml package
2.5 mm thick x 2 x 150 mm wide with 20 mm Fillet	0.7 Linear Meter per 600ml package
2.5mm thick x 20 mm Fillet	3 Linear Meters per 600ml package

Coverage information are typical and based on the smooth surface and will vary with surface texture

### Mixing

PREPRUFE® DLM is mono-component and doesn't require mixing on site.

### Application

Apply PREPRUFE® DLM with a solid barrel gun and trowel the product to achieve a minimum thickness of 2.5 mm. Once applied, PREPRUFE® DLM will create a dry skin layer within one hour at normal ambient temperatures which will allow the product to be covered and to continue the works on site.

Material which has hardened on the installation tools must be discarded, and the tip of the gun's nozzle must be trimmed before every application.

In case of application of PREPRUFE® 800PA, PREPRUFE® Tape and BITUTHENE® membranes on top of already cured PREPRUFE® DLM, it is required to prime the cured product with BITUTHENE® Primer W2.

Avoid thick layers of product, as in depth curing will take longer. To speed up the curing time, you may vaporize some water on the applied product.

At temperatures below +10°C, store overnight at +20°C to improve product's workability.

Clean tools and equipment with solvent tool cleaner before PREPRUFE® DLM has cured.

### Damage Repair

- Damaged PREPRUFE® DLM can be repaired using PREPRUFE® DLM. Fully or partially cured PREPRUFE® DLM can be repaired using fresh PREPRUFE® DLM which will bond very well to already applied PREPRUFE® DLM. The PREPRUFE® DLM that needs repairing needs to be degreased and dust free.

- PREPRUFE® DLM can be used to re-bond PREPRUFE® membranes on vertical when it has been de-bonded accidentally. After application of PREPRUFE® DLM, apply a water mist to the surface of PREPRUFE® DLM to initiate the curing process of PREPRUFE® DLM. Consequently apply the PREPRUFE® membrane on the PREPRUFE® DLM. Ensure good contact between PREPRUFE® DLM and the PREPRUFE® membrane.

## UV Protection

PREPRUFE® DLM is not designed for permanently exposed applications, it should be covered within 56 days of application.

## Health and Safety

Read the product carton and Safety Data Sheet (SDS) before use. Users must comply with all risk and safety phrases. SDS's can be obtained from GCP Applied Technologies or from our web site at [gcpat.com](http://gcpat.com).

[gcpat.se](http://gcpat.se) | Sverige kundservice: +46 (0) 4216 7800

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

BITUTHENE and PREPRUFE are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2021 GCP Applied Technologies Inc. All rights reserved.

0621 PREPRUFE DLM\_UK

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP Sweden AB, Gärdesvägen 3, 444 31 Stenungsund

Detta dokument är endast aktuellt från och med det senast uppdaterade datumet som anges nedan och gäller endast för användning i Sverige. Det är viktigt att du alltid hänvisar till den information som för närvarande finns tillgänglig på webbadressen nedan för att ge den mest aktuella produktinformationen vid användningstillfället. Ytterligare litteratur såsom entreprenörshandböcker, tekniska bulletiner, detaljritningar och detaljrekommendationer och andra relevanta dokument finns också på [www.gcpat.se](http://www.gcpat.se). Information som finns på andra webbplatser får inte åberopas, eftersom de kanske inte är aktuella eller tillämpliga på villkoren i din plats och vi tar inget ansvar för innehållet. Om det finns några konflikter eller om du behöver mer information, kontakta GCP kundservice.

Last Updated: 2022-02-03

[gcpat.se/solutions/products/preprufe-pre-applied-waterproofing-solutions/preprufe-dlm](http://gcpat.se/solutions/products/preprufe-pre-applied-waterproofing-solutions/preprufe-dlm)